

# 光学特性データ

測定サンプル | スノーマット100LS(S10)

STD. WHITE=	11.505
PG(H)=	1.00
$\alpha$ (H)R=	85.00
$\alpha$ (H)L=	85.00
$\beta$ (H)R=	-
$\beta$ (H)L=	-

( $\alpha$ ) = 半値角(ピークゲインの1/2の値)  
 ( $\beta$ ) = 1/3値角(ピークゲインの1/3の値)

HORIZONTAL		
角度	nt	Gs
-80.0°	8.693	0.76
-75.0°	9.14	0.79
-70.0°	9.332	0.81
-65.0°	9.524	0.83
-60.0°	9.716	0.84
-55.0°	9.843	0.86
-50.0°	9.907	0.86
-45.0°	10.099	0.88
-40.0°	10.163	0.88
-35.0°	10.227	0.89
-30.0°	10.419	0.91
-25.0°	10.61	0.92
-20.0°	10.866	0.94
-15.0°	11.186	0.97
-10.0°	11.233	0.98
-5.0°	11.425	0.99
-2.5°	11.505	1.00
+2.5°	11.51	1.00
+5.0°	11.423	0.99
+10.0°	11.221	0.98
+15.0°	11.058	0.96
+20.0°	10.738	0.93
+25.0°	10.547	0.92
+30.0°	10.419	0.91
+35.0°	10.227	0.89
+40.0°	10.099	0.88
+45.0°	10.035	0.87
+50.0°	9.907	0.86
+55.0°	9.779	0.85
+60.0°	9.716	0.84
+65.0°	9.524	0.83
+70.0°	9.322	0.81
+75.0°	9.076	0.79
+80.0°	8.565	0.74

