

光学特性データ

Sample : FILMSCREEN-200

Data : 97.03.17

STD . WHITE =	180
PG (H) =	2.15
PG (V) =	0.00
(H) R =	+ 25.00°
(H) L =	- 20.00°
(V) R =	+ 0.00°
(V) L =	- 0.00°
(H) R =	+ 35.00°
(H) L =	- 30.00°
(V) R =	+ 0.00°
(V) L =	- 0.00°

() = 半値角(ビークの1/2の値)

() = 1/3角(ピークの1/3の値)

HORIZONTAL					
Angle	nt	Gs	Angle	nt	Gs
- 85.0°	5.00	0.03	+ 2.5°	387.00	2.15
- 80.0°	12.00	0.07	+ 5.0°	377.00	2.09
- 75.0°	28.00	0.16	+ 10.0°	337.00	1.87
- 70.0°	37.00	0.21	+ 15.0°	283.00	1.57
- 65.0°	41.00	0.23	+ 20.0°	230.00	1.28
- 60.0°	46.00	0.26	+ 25.0°	182.00	1.01
- 55.0°	53.00	0.29	+ 30.0°	145.00	0.81
- 50.0°	62.00	0.34	+ 35.0°	116.00	0.64
- 45.0°	74.00	0.41	+ 40.0°	93.00	0.52
- 40.0°	90.00	0.50	+ 45.0°	77.00	0.43
- 35.0°	111.00	0.62	+ 50.0°	64.00	0.36
- 30.0°	138.00	0.77	+ 55.0°	55.00	0.31
- 25.0°	176.00	0.98	+ 60.0°	48.00	0.27
- 20.0°	222.00	1.23	+ 65.0°	42.00	0.23
- 15.0°	278.00	1.54	+ 70.0°	35.00	0.19
- 10.0°	331.00	1.84	+ 75.0°	20.00	0.11
- 5.0°	374.00	2.08	+ 80.0°	7.00	0.04
- 2.5°	387.00	2.15	+ 85.0°	1.00	0.01

