

光学特性データ

Sample : SILKY MATTE
 Data : 99.06.22

STD . WHITE =	180
PG (H) =	1.58
PG (V) =	0.00
(H) R =	+ 45.00°
(H) L =	- 40.00°
(V) R =	+ 0.00°
(V) L =	- 0.00°
(H) R =	+ 85.00°
(H) L =	- 80.00°
(V) R =	+ 0.00°
(V) L =	- 0.00°

() = 半値角(ビ-ケインの1/2の値)
 () = 1/3角(ビ-ケインの1/3の値)

HORIZONTAL					
Angle	nt	Gs	Angle	nt	Gs
- 85.0°	67.00	0.37	+ 2.5°	282.00	1.57
- 80.0°	108.00	0.60	+ 5.0°	269.00	1.49
- 75.0°	116.00	0.64	+ 10.0°	235.00	1.31
- 70.0°	123.00	0.68	+ 15.0°	206.00	1.14
- 65.0°	127.00	0.71	+ 20.0°	184.00	1.02
- 60.0°	132.00	0.73	+ 25.0°	167.00	0.93
- 55.0°	135.00	0.75	+ 30.0°	157.00	0.87
- 50.0°	138.00	0.77	+ 35.0°	150.00	0.83
- 45.0°	142.00	0.79	+ 40.0°	144.00	0.80
- 40.0°	146.00	0.81	+ 45.0°	141.00	0.78
- 35.0°	152.00	0.84	+ 50.0°	137.00	0.76
- 30.0°	159.00	0.88	+ 55.0°	134.00	0.74
- 25.0°	171.00	0.95	+ 60.0°	131.00	0.73
- 20.0°	188.00	1.04	+ 65.0°	127.00	0.71
- 15.0°	211.00	1.17	+ 70.0°	122.00	0.68
- 10.0°	240.00	1.33	+ 75.0°	115.00	0.64
- 5.0°	273.00	1.52	+ 80.0°	107.00	0.59
- 2.5°	285.00	1.58	+ 85.0°	84.00	0.47

