

光学特性データ

Sample : テックスクリーン200 for3D

Data : 01.11.15

| | |
|---------------|----------|
| STD . WHITE = | 180 |
| PG (H) = | 2.06 |
| PG (V) = | 0.00 |
| (H) R = | + 25.00° |
| (H) L = | - 25.00° |
| (V) R = | + 0.00° |
| (V) L = | - 0.00° |
| (H) R = | + 35.00° |
| (H) L = | - 35.00° |
| (V) R = | + 0.00° |
| (V) L = | - 0.00° |

() = 半値角(ビーム径の1/2の値)

() = 1/3角(ビーム径の1/3の値)

| HORIZONTAL | | | | | |
|------------|--------|------|---------|--------|------|
| Angle | nt | Gs | Angle | nt | Gs |
| - 85.0° | 10.00 | 0.06 | + 2.5° | 370.00 | 2.06 |
| - 80.0° | 15.00 | 0.08 | + 5.0° | 364.00 | 2.02 |
| - 75.0° | 24.00 | 0.13 | + 10.0° | 331.00 | 1.84 |
| - 70.0° | 30.00 | 0.17 | + 15.0° | 286.00 | 1.59 |
| - 65.0° | 38.00 | 0.21 | + 20.0° | 238.00 | 1.32 |
| - 60.0° | 44.00 | 0.24 | + 25.0° | 195.00 | 1.08 |
| - 55.0° | 52.00 | 0.29 | + 30.0° | 156.00 | 0.87 |
| - 50.0° | 63.00 | 0.35 | + 35.0° | 123.00 | 0.68 |
| - 45.0° | 77.00 | 0.43 | + 40.0° | 99.00 | 0.55 |
| - 40.0° | 95.00 | 0.53 | + 45.0° | 79.00 | 0.44 |
| - 35.0° | 122.00 | 0.68 | + 50.0° | 64.00 | 0.36 |
| - 30.0° | 152.00 | 0.84 | + 55.0° | 53.00 | 0.29 |
| - 25.0° | 190.00 | 1.06 | + 60.0° | 44.00 | 0.24 |
| - 20.0° | 233.00 | 1.29 | + 65.0° | 38.00 | 0.21 |
| - 15.0° | 282.00 | 1.57 | + 70.0° | 33.00 | 0.18 |
| - 10.0° | 326.00 | 1.81 | + 75.0° | 29.00 | 0.16 |
| - 5.0° | 362.00 | 2.01 | + 80.0° | 16.00 | 0.09 |
| - 2.5° | 371.00 | 2.06 | + 85.0° | 10.00 | 0.06 |

