

光学特性データ

Sample : ホワイトマットアドバンス

Data : 04.10.13

STD. WHITE = 180
PG (H) = 0.84
PG (V) = 0.00
(H) R = + 85.00°
(H) L = - 80.00°
(V) R = + 0.00°
(V) L = - 0.00°
(H) R = + 0.00°
(H) L = - 0.00°
(V) R = + 0.00°
(V) L = - 0.00°

() = 半値角(ビークインの1/2の値)
 () = 1/3角(ビークインの1/3の値)

HORIZONTAL					
Angle	nt	Gs	Angle	nt	Gs
- 85.0°	57.00	0.32	+ 2.5°	152.00	0.84
- 80.0°	88.00	0.49	+ 5.0°	149.00	0.83
- 75.0°	114.00	0.63	+ 10.0°	147.00	0.82
- 70.0°	127.00	0.71	+ 15.0°	145.00	0.81
- 65.0°	129.00	0.72	+ 20.0°	143.00	0.79
- 60.0°	131.00	0.73	+ 25.0°	142.00	0.79
- 55.0°	133.00	0.74	+ 30.0°	140.00	0.78
- 50.0°	134.00	0.74	+ 35.0°	139.00	0.77
- 45.0°	136.00	0.76	+ 40.0°	137.00	0.76
- 40.0°	137.00	0.76	+ 45.0°	135.00	0.75
- 35.0°	138.00	0.77	+ 50.0°	134.00	0.74
- 30.0°	140.00	0.78	+ 55.0°	132.00	0.73
- 25.0°	142.00	0.79	+ 60.0°	130.00	0.72
- 20.0°	144.00	0.80	+ 65.0°	128.00	0.71
- 15.0°	145.00	0.81	+ 70.0°	125.00	0.69
- 10.0°	147.00	0.82	+ 75.0°	120.00	0.67
- 5.0°	150.00	0.83	+ 80.0°	95.00	0.53
- 2.5°	152.00	0.84	+ 85.0°	64.00	0.36

