

光学特性データ

測定サンプル | ホワイトマット(W)

STD. WHITE=	11.505
PG(H)=	0.90
α (H)R=	85.00
α (H)L=	85.00
β (H)R=	-
β (H)L=	-

(α) = 半値角(ピークゲインの1/2の値)
 (β) = 1/3値角(ピークゲインの1/3の値)

HORIZONTAL		
角度	nt	Gs
-80.0°	8.244	0.72
-75.0°	8.659	0.75
-70.0°	8.879	0.77
-65.0°	9.102	0.79
-60.0°	9.239	0.80
-55.0°	9.268	0.81
-50.0°	9.396	0.82
-45.0°	9.460	0.82
-40.0°	9.524	0.83
-35.0°	9.576	0.83
-30.0°	9.643	0.84
-25.0°	9.655	0.84
-20.0°	9.716	0.84
-15.0°	9.779	0.85
-10.0°	9.843	0.86
-5.0°	9.907	0.86
-2.5°	10.329	0.90
+2.5°	10.111	0.88
+5.0°	9.971	0.87
+10.0°	9.843	0.86
+15.0°	9.779	0.85
+20.0°	9.705	0.84
+25.0°	9.632	0.84
+30.0°	9.588	0.83
+35.0°	9.524	0.83
+40.0°	9.524	0.83
+45.0°	9.464	0.82
+50.0°	9.332	0.81
+55.0°	9.268	0.81
+60.0°	9.204	0.80
+65.0°	9.076	0.79
+70.0°	8.949	0.78
+75.0°	8.757	0.76
+80.0°	8.5498	0.74

