


光学特性データ

測定サンプル | テックスクリーン100(TS10)

STD. WHITE=	11.505
PG(H)=	1.00
α (H)R=	45.00
α (H)L=	45.00
β (H)R=	65.00
β (H)L=	65.00

(α) = 半値角(ピークゲインの1/2の値)
 (β) = 1/3値角(ピークゲインの1/3の値)



HORIZONTAL		
角度	nt	Gs
-80.0°	1.795	0.16
-75.0°	2.557	0.22
-70.0°	2.876	0.25
-65.0°	3.579	0.31
-60.0°	4.027	0.35
-55.0°	4.346	0.38
-50.0°	5.105	0.44
-45.0°	5.625	0.49
-40.0°	6.072	0.53
-35.0°	7.159	0.62
-30.0°	7.926	0.69
-25.0°	8.949	0.78
-20.0°	10.099	0.88
-15.0°	10.547	0.92
-10.0°	11.058	0.96
-5.0°	11.251	0.98
-2.5°	11.505	1.00
+2.5°	11.504	1.00
+5.0°	11.377	0.99
+10.0°	11.186	0.97
+15.0°	10.61	0.92
+20.0°	9.907	0.86
+25.0°	8.629	0.75
+30.0°	7.734	0.67
+35.0°	6.775	0.59
+40.0°	6.008	0.52
+45.0°	5.305	0.46
+50.0°	4.73	0.41
+55.0°	4.155	0.36
+60.0°	3.943	0.34
+65.0°	3.196	0.28
+70.0°	2.748	0.24
+75.0°	2.301	0.20
+80.0°	1.543	0.13